



ELK
Asia Pacific Journals

www.elkjournals.com

STUDY OF NANO-EMBEDMENTS ON ORDINARY CEMENT COMPOSITES

Mainak Ghosal Research Scholar, Indian Institute of Engineering Science & Technology West Bengal, India	Prof. Arun Kumar Chakraborty Associate Professor, Dept. of Civil Engineering, Indian Institute of Engineering Science & Technology West Bengal, India
---	---

ABSTRACT

One of the most interesting research fields of recent time is the study of reaction mechanism of nano embedments in cement composites. Cement composites prepared with river sand as per Indian standards with and without Nanoparticles showed an increase of 31% in compressive strength at 7 days & 32% at 28 days & 59% at 90 days respectively. However, the gain fell to 8% at 180 days when compared to ordinary cement composites at 0.75% nS optimization w.r.to cement wt. Similarly, Nano Carbon tube embedments showed a decrease of 16% at 7 days, 37% increase at 28 days, 14% increase at 90 days & 3% increase at 180 days when compared to ordinary controlled cement composite after dispersion in Super Plasticizer – Poly Carboxylate Ether at 0.02% optimization of Nanotubes w.r.to cement wt.

Keywords: Embedments, Cement, Nano, Strength, Tubes

1.0 INTRODUCTION

Nanoparticles were found having applications in various fields of life starting from energy sector to electronics to civil-construction to textiles. The emergence of this technology was caused in 1980s due to the convergence of experimental advances like invention of Scanning Tunneling Microscopy (1981) and discovery of Fullerenes (1985) which lead to the awarding of the Nobel Prize in 2010 in Physics for the

discovery of Fullerenes. In fact it was Nanotechnology that allowed creation of iPods, iPhones and all sort of these “i” products which in a way completely changed the IT and electronics sectors. So why can't applications of Nanotechnology do the same to our conservative construction sector now? There have been many successful NT based applications which could have been almost impossible without utility of nano sized particles. For example, anti-scratch paints,



ELK
Asia Pacific Journals

www.elkjournals.com

anti-bacterial paints, anti-fouling concrete, dirt repellent textiles, clothes that need no ironing, non-reflective glasses, wonder drugs etc. are only the tip of the iceberg. It is a surprise to learn that the Romans and Chinese were using nanoparticles thousands of years ago. Carbon black the substance that makes our tyres black and improves the wear resistance of the rubber was known since 1920s. Of course they were not aware that they were using nanotechnology, as they had no control over particle size, or even any knowledge of the nanoscale as currently defined.

"Nanotechnology is the base technology of an industrial revolution in the 21st century. Those who control nanotechnology will lead the industry."

-- *Michiharu Nakamura, Executive VP at Hitachi*

Nano is a Greek word and means "Dwarf". Carbon Nanotubes was first discovered by Russian scientists L. V. Radushkevich & V. M. Lukyanovich in 1952.

The Nanoparticle size which is below One billionth of a meter is produced as nano-additives are from traditional cement, silica (quartzite sand) or even fly ash. For larger scale, nano-Silica (nS) [the first nanomaterial to be used in construction] are produced from *Vaporization of silica* or by *feeding worms with rice husk* or by *precipitation method*

while techniques have been developed to produce nanotubes in sizeable quantities, including arc discharge, laser ablation, high-pressure carbon monoxide disproportionation (HiPco), and chemical vapor deposition (CVD).

A Nano additive as cement replacement in very insignificant dosages changes the hydration kinetics of entire cementitious system resulting in the improvement in the compressive strength of paste, mortar and concrete. Additionally, the rheology of paste, mortar & concrete is influenced with nano-additions. It also improves the microstructure of the concrete system. Work presented by many authors reveals that the nano-additives



ELK
Asia Pacific Journals

www.elkjournals.com

improve the performance of concrete resulting in High Performance Concrete (HPC) or Ultra High Performance Concrete (UHPC) and in turn making concrete durable. Though Nano-Silica (nS) is now commercially available in India but the production of Carbon Nano-Tubes (CNT) in the whole world is to the tune of several hundred Kilograms per year, thus making it very costly. So it is clear that the impact of nanotechnology on cementitious is at present mainly at the research level. These advances in scientific understanding need to be transferred into the field by introduction of technical and safety standards of the material used.

The first patent on nano-enabled cement was published in 1996 and since then it has seen an exponential rise after 2007. China has emerged as the major contributor in this area with 41% of global patents filings. The emergence of nanotechnology in cement industry has already shown a remarkable impact on mechanical and other properties of cementitious materials with patented

commercial products such as NanoCrete, Cor-Tuf®, HuberCrete®, Alpol, Nycon-G Nano, TioCem, TxActive, MC-Special DM etc. are already available in market. Naga Nanotech etc. apart from big commercial houses like Reliance, TataGroup, Mahindra & Mahindra exploring NT options. Many scientists believe that R&D in nanoscience and technology must be promoted at central and state universities since that allows an opportunity for students undertaking bachelors and masters programs. Accordingly, Dr Kalam, the nation's then president and renowned space scientist assumed the role of promoting nanotechnology at several national academic and other forums. His pro nanotechnology oratory and stance coupled with vision for establishing India as a "nanotechnology hub" has influenced policy makers and academia to strenuously emphasize on this emerging science and technology. The Budget allocation for (National Nano Science & Technology Mission) NSTM amongst all the schemes in the 10th five year



ELK
Asia Pacific Journals

www.elkjournals.com

plan was second. Construction projects today are increasingly required to meet stringent building codes and energy regulations which is fuelling an industry transition to use the next generation *nanomaterials*. The Twelfth Five Year Plan emphasized use of new materials & technology for the Ministry of Roads & Surface Transport (MORSTH). The emergence of nanotechnology in India has witnessed a diverse set of players ranging from domains like agriculture, water, health, energy, & environment to industries like pharmaceuticals, automobiles, electronics, textiles, chemicals & manufacturing (of which construction is a small part), IT & biotechnology. Among the government agencies, besides Department of Science & Technology (DST) other agencies include Council of Scientific & Industrial Research (CSIR), Dept. of Bio-Technology (DBT), and agencies under Ministry of Information & Communication Technology, Ministry of Family Health & Welfare, Ministry of Defence, and Ministry of New & Renewable Energy are engaged with the

promotion of NT in terms of R&D activities. Also there are private companies in India those are engaged in NT such as Beechems, NanoBeach, Monad Nanotech, NanoShell, NagaNanotech, Qtech Nanosystems, apart from big commercial houses like Reliance, Tata Group, Mahindra & Mahindra, GoodYear, Bridgestone etc. are exploring NT options.

2.0 LITERATURE REVIEW

Belkowitz, S.J. & Armentrout, D.¹ developed relationships to distinguish the benefits when using different sizes of nano-silica (nS) in cement hydration paste through experimenting & measuring the heat of hydration of multiple mix designs and showed that as silica particles decreased in size with increased size distribution the C-S-H became more rigid and in turn increasing the compressive strength.

Quercia, G. & Brouwers, H.J.H² aimed to present in their paper the nS production process from olivine



ELK
Asia Pacific Journals

www.elkjournals.com

dissolution, their addition and their application in concrete.

Valipour.M et al³ studied the influence of nS addition on properties of concrete when compared with silica fumes (SF) through measurement of compressive strength, electrical resistivity & gas permeability. The results show that replacement of a portion of SF with nS is more active in early age due to larger specific surface & fineness and will also improve the durability aspects of HPC.

Kumar,S. et al⁴ discussed the effect of Multiwalled Carbon Nanotubes(MWCNT) on strength characteristics of hydrated Portland cement paste by mixing various proportions of MWCNT and found an increase in compressive and tensile strength of 15% and 36% at 28 days.

Maheswaran,S et al⁵ attempted to highlight the influence of Ns towards pore filling effect and its pozzolonic activity with cement for improvement of mechanical properties and durability aspects. The paper also says that

there is a scope for development of crack free concrete.

Yang,H⁶ presented the laboratory investigations that when nano silicon powder mixing content is 0.5%,0.75% & 1.0% compared with ordinary concrete ,the bending tensile strength at 28 days were increased by 3.2%,7.5% & 4.0% and the shrinkage rate at the same age reported increase by 75.5%,127.1% & 163.0%.

Yuvraj,S⁷ described when nS is added it makes the concrete less alkaline as C-H in concrete is reduced which reduces the corrosion of steel bars. He also added that more C-S-H is produced at the Nano scale thus increasing the compressive strength.

Abyaneh, M.R.J. et al⁸ investigated the compressive strength, electrical resistivity and water absorption of the concrete containing nS and micro-silica at 7,14,28 days and reported that concrete with micro-silica and nS have high compressive strength than with concrete with only micro-silica. He further deliberated that that specimens with



ELK
Asia Pacific Journals

www.elkjournals.com

2% nS and 10% micro-silica have less water absorption and more electrical resistance in comparison with others.

Madhavi, T. et al⁹ found an increase in compressive and split-tensile strengths of samples with increasing MWCNT. 0.045% of MWCNT has improved the 28 days compressive strength by 27% while the split tensile strength increased by 45%. Crack propagation was reduced and water absorption decreased by 17% at 28 days curing.

Rajmane, N.P. et al¹⁰ showed that nS cannot be used as an admixture to improve the microstructure of the cement composites (with and without 5% SF) at the w/c ratio of 0.5.

2.0 SCOPE OF PRESENT WORK

The nano-Silica (nS) and Carbon-Nanotubes (Multi-walled, Industrial grade) are a product of nanotechnology and are commercially available. The overall aim of the experimental programme of this research is to produce a workable high performance Cement composites

that would provide both long-term and high-early-strength and that would meet the durability requirements of most practical constructions in an aggressive environment such as India.

4.0 EXPERIMENTAL PROGRAMME –

Materials used:

1. Cement – Ambuja OPC Types
2. Reinforcement Bar -- NA
3. Sone Aggregate -- NA
4. Fine Aggregate -- Natural (River) Sand
5. Water -- Drinking (Tap) Water
6. Chemical Admixture -- Chryso
7. Nano Additives -- Nano Silica (nS) & Multi-Walled Carbon Nanotubes (MWNTs)

(I) The first test procedure involved testing Nano-Silica (XLP, XTX, XFXLa — Supplied by M/s BEECHEMS, Kanpur, India) in variable quantities (0%, 0.5%, 0.75%, 1.0%, 1.25%, 1.5% by cement wt.) in Ordinary Portland



ELK
Asia Pacific Journals

www.elkjournals.com

Cement(OPC-Ambuja make) in a compression testing machine.

Test Procedure(I):Mortar cubes of 70.7mmX70.7mmX70.7mm dimensions are filled with 1 part of Cement + 3parts of River Sand with Water added, according to the standard formula $P' = (P/4 + 3)(1 \text{ part Cement} + 3\text{parts Sand})$. Here $P' = \text{Quantity of water}$ & $P = \text{Consistency of Cement used}$ i.e.

Amount of water used to make 300gms cement paste to support a penetration of 5-7mm in a standard Vicat mould with a Vicat needle. Now we would be testing the Compressive Strength of both composite & ordinary Cement Mortar after 1day, 3days, 7days, 28days, 90days, 180days, 365days ordinary curing in a COMPRESSION CUBE CRUSHING/TESTING M/C.

Mix Design (for Ordinary Portland Cement-43 Grade Ambuja):

(A) For 0.0% Nano-Silica: Standard weight of Cement taken for 12 nos. Moulds = 12X200=2400gms Weight of River Sand (Zone-III) a/c to 1:3::Cement:Sand-ratio=3X12X200=7200gms. Weight of Water added (comes to be) = $(30/4 + 3)(2400 + 7200)/100 = 1008\text{gms (ml.)}$ *As $P = 30\%$ (As Laboratory Test suggests)

(B) For 0.5% wt. of Nano-Silica w.r.to Cement wt. Standard weight of Cement taken for 12 nos. Moulds = 12X200=2400gms Weight of River Sand a/c to 1:3 ratio=3X12X200=7200gms. Weight of Water added (comes to be) = $(30/4 + 3)(2400 + 7200)/100 = 1008\text{gms (ml.)}$ 0.5% XTX = $0.5/100 \times 2400 = 12\text{gms}$ of Nano-

Silica required $\equiv 29.5\text{gms}$ of XTX $\equiv 25.4\text{ml}$ of XTX.

(@ % wt. of solid content in XTX=40.74%; Density (XTX) = 1.16gms/cc.) Net Water added = $1008 - 25.4 = 982.6\text{ml}$. ~983ml.

(C) For 0.75% wt. of Nano-Silica w.r.to Cement wt. Standard weight of Cement taken for 12 nos. Moulds = 12X200=2400gms Weight of River Sand a/c to 1:3 ratio=3X12X200=7200gms. Weight of Water added (comes to be) = $(30/4 + 3)(2400 + 7200)/100 = 1008\text{gms (ml.)}$ 0.75% XTX = $0.75/100 \times 2400 = 18\text{gms}$ of Nano-

Silica required $\equiv 44.18\text{gms}$ of XTX $\equiv 38.08\text{ml}$ of XTX.

(@ % wt. of solid content in XTX=40.74%; Density (XTX) = 1.16gms/cc.) Net Water added = $1008 - 38 = 970\text{ml}$.



ELK
Asia Pacific Journals

www.elkjournals.com

(D) For 1.00% wt. of Nano-Silica w.r.to Cement wt. Standard weight of Cement taken for 12 nos. Moulds = $12 \times 200 = 2400$ gms Weight of River Sand a/c to 1:3 ratio = $3 \times 12 \times 200 = 7200$ gms. Weight of Water added (comes to be) = $(30/4 + 3) (2400 + 7200) / 100 = 1008$ gms (ml.) 1.00% XTX = $1.00 / 100 \times 2400 = 24$ gms of Nano-

Silica required $\equiv 59$ gms of XTX $\equiv 50.78$ ml. of XTX.

(@ % wt. of solid content in XTX = 40.74%; Density (XTX) = 1.16gms/cc.) Net Water added = $1008 - 50.78 = 957.22$ ml.

(E) For 1.25% wt. of Nano-Silica w.r.to Cement wt. Standard weight of Cement taken for 12 nos. Moulds = $12 \times 200 = 2400$ gms Weight of River Sand a/c to 1:3 ratio = $3 \times 12 \times 200 = 7200$ gms. Weight of Water added (comes to be) = $(30/4 + 3) (2400 + 7200) / 100 = 1008$ gms (ml.) 1.25% XTX = $1.25 / 100 \times 2400 = 30$ gms of Nano-

Silica required $\equiv 76.37$ gms of XTX $\equiv 63.5$ ml. of XTX.

(@ % wt. of solid content in XTX = 40.74%; Density (XTX) = 1.16gms/cc.) Net Water added = $1008 - 63.5 = 944.5$ ml.

(F) For 1.5% wt. of Nano-Silica w.r.to Cement wt. Standard weight of Cement taken for 12 nos. Moulds = $12 \times 200 = 2400$ gms Weight of

River Sand a/c to 1:3 ratio = $3 \times 12 \times 200 = 7200$ gms. Weight of Water added (comes to be) = $(30/4 + 3) (2400 + 7200) / 100 = 1008$ gms (ml.) 1.5% XFXLa = $1.5 / 100 \times 2400 = 36$ gms of Nano-

Silica required $\equiv 85.85$ gms of XFXLa $\equiv 69.23$ ml. of

XFXLa. (@ % wt. of solid content in XFXLa = 41.935%; Density (XFXLa) = 1.24gms/cc.) Net Water added = $1008 - 69.23 = 938.76$ ml.

(II) The second test procedure involved testing Carbon-Nanotubes (Multiwalled, Industrial Grade — Supplied by M/s NANOSHEL, Panchkula, Haryana, India) dispersed in Superplasticizer (Polycarboxylate Ether (PCE) supplied by CHRYSO at 2% by wt. of cement) in an optimum dosage (0.02% by wt. of cement as per Literature Review) in Ordinary Portland Cement (OPC-Ambuja make) in a compression testing machine.

Test Procedure (II): Mortar cubes of 70.7mm X 70.7mm X 70.7mm dimensions are filled with 1 part of Cement + 3 parts of River Sand with Water added, according to the standard formula $P'' = (P/4 + 3)$ (1 part Cement + 3 parts Sand). Here $P'' =$ Quantity of water & $P =$ Consistency of Cement used. i.e., amount of water used to make 300gms



ELK
Asia Pacific Journals

www.elkjournals.com

cement paste to support a penetration of 5-7mm in a standard Vicat mould with a Vicat needle. Now we would be testing the Compressive Strength of both composite & ordinary Cement Mortar after 1day, 3days,

7days, 28days, 90days, 180days, 365days ordinary curing in a COMPRESSION CUBE CRUSHING/TESTING M/C.

5.0 TEST RESULTS –

The following **Table1** shows the Test Results obtained for nS embedment.

Sl	% nS in Cem ent Type (OP C)	1 day streng th (N/m m ²)	% incre ase	3 day streng th (N/m m ²)	% incre ase	7 day streng th (N/m m ²)	% incre ase	28 day streng th (N/m m ²)	% incre ase	90 day streng th (N/m m ²)	% incre ase	180 day streng th (N/m m ²)	% incre ase
1.	0	19.59	--	23.72	--	21.08		31.89	--	31.2	--	30.01	--
2.	0.5	16.28	-16.89	27.16	14.5	23.85	13.14	35.51	11.35	41.3	32.7	27.47	-9.2
3.	0.75	16.83	-14.08	30.10	26.89	27.73	31.54	42.27	32.55	49.85	59.8	32.52	8.4



ELK
Asia Pacific Journals

www.elkjournals.com

4.	1.0	18.36	-6.27	19.38	-	25.07	18.9	37.36	17.1	42.98	37.7	33.68	12.2
					18.2		3		5				
					9								
5.	1.25	20.16	2.91	27.54	16.1	23.17	9.91	30.85	3.26	39.45	26.4	35.24	17.4
					0								
6.	1.5	20.69	5.62	23.35	-1.56	23.81	12.9	37.79	18.5	33.42	7.12	31.23	4.07
							5						

The following **Table 2** shows the Test Results obtained for CNT embedment.

Sl	% CNT	1 day	%	3 day	%	7 day	%	28	%	90	%	180	%
No.	Cement	stren	in	stren	in	stren	in	day	in	day	in	day	in
	Type	gth	cre	gth	ase	gth	ase	stren	ase	stren	ase	stren	ase
	OPC	(N/m		(N/m		(N/m		(N/m		(N/m		(N/m	
		m ²)		m ²)		m ²)		m ²)		m ²)		m ²)	
1.	OPC	19.59	--	23.47	--	21.3	--	35.2	--	24.1	--	30.0	--
						3				4		1	



ELK
Asia Pacific Journals

www.elkjournals.com

2.	OPC(1 % PCE)	Cubes could't be demo ulded		Cubes could't be demo ulded		18.8 8	- 10.4	28.7 3	- 9.91	36.0 3	15.4 8	33.2 5	10
3.	OPC(1 % PCE+0 .02% CNT)	Cubes could't be demo ulded		11.03 - 53.5	- 9	17.6 9	- 16.1	43.7 5	37.2	35.5 9	14.0 7	30.8 9	3
4.	OPC(1 % PCE+0 .05% CNT))	Cubes could't be demo ulded		5.38 - 66.4	- 9	27.1 9	28.9	34.8 8	9.37	31.8 5	2.08	38.5 5	23.5 5
5.	OPC(1 % PCE+0	Cubes could't be		14.21 - 40.1	- 9	21.6 9	2.89	24.8 3	- 22.1	31.5 4	0.96	30.1 6	- 3.33



ELK
Asia Pacific Journals

www.elkjournals.com

	.1%	demo											
	CNT))	ulded											

5.1 Discussion of Test Results:-

Table 1 shows the compressive strength results of Ordinary Portland Cement for various percentages of nano-silica. For 1 day, the maximum strength has been observed for 1.5% nS with an increase of 5.62% from the controlled specimen. For 3 days, the maximum strength has been observed for 0.75% nS with an increase of 26.89% from the controlled specimen. For 7 days also, the maximum strength has been observed for 0.75% nS increasing about 27.73% from the controlled specimen. For 28 days again, the maximum strength has been observed for 0.75% nS with an increase of 17.15% from the controlled specimen. For 90 days, the maximum strength has been observed for 1.0% nS with an increase of 35.2% from the controlled specimen. For 180 days the maximum strength was found for 1.25% nS with an increase of 17.4%.

Table 2 shows the compressive strength results of Ordinary Portland Cement for various percentages of carbon Nanotubes dispersed in PCE. At 1 day no cube was found to get demoulded for testing. The 28

days maximum strength was 43.75 MPa and was found for 0.02% CNTs with a 37% increase w.r.to ordinary cement mortar. However, at latter ages the strength decreases.

“ Soon researchers will bring us devices that can translate foreign languages as fast as you can talk; materials 10 times stronger than steel at a fraction of the weight; and, this is unbelievable to me, molecular computers the size of at eardrop with the power of today's fastest supercomputers.”

---- Bill Clinton.

6.0 CONCLUSIONS-

1. An optimization of nS was found at 0.75% of cement wt. for maximum mechanical strength at 28 days.
2. An optimization of CNTs was found at 0.02% of cement wt. at 1% Super plasticizer w.r.to cement wt. for



ELK
Asia Pacific Journals

www.elkjournals.com

maximum mechanical strength at 28 days.

3. The strength decreases with nano embedment at later ages. This may be attributed to the fact that Nanoparticles tend to get oxidized at that period of time.

7.0 REFERENCES

- [1] Belkowitz, S.J. & Armentrout, D. (2010), „An Investigation of Nano Silica in the Cement Hydration Process“, Concrete Sustainability Conference, National Ready Mixed Concrete Association, Europe.
- [2] Quercia, G. & Brouwers, H.J. (2010), Application of nano-silica (nS) in concrete mixtures “8th fib PhD Symposium in Kgs. Lyngby, Denmark, June 2 – 23, 2010.
- [3] Valipour, M. et al. (2010), „Comparative study of nano-SiO₂ and silica fume on gas permeability of high performance concrete (HPC)“ © 2010 Korea Concrete Institute.
- [4] Kumar, S. et al. (2012), „Effect of Multiwalled Carbon Nanotubes on Mechanical Strength of Cement Paste“, Journal of Materials in Civil Engineering, 24(1), 84-91.
- [5] Maheswaran, S. et al. (2012). „An Overview on the Influence of Nano Silica in Concrete Research Initiative“, Research Journal of Recent Sciences, Vol. 2 (ISC-2012), 17-24.
- [6] Yang, H. (2012), „Strength and Shrinkage Property of Nano Silica Powder Concrete“, 2nd International Conference on Electronic & Mechanical Engineering & Information Technology, China.
- [7] Yuvraj, S. (2012), „Experimental Research On Improvement Of Concrete Strength And Enhancing The Resisting Property Of Corrosion And Permeability By The Use Of Nano Silica Flyashed Concrete“. International Journal of Emerging Technology and Advanced Engineering, Vol. 2, Issue 6, June 2012.
- [8] Abyaneh, M.R.J. et al. (2013). „Effects of Nano-Silica on Permeability of Concrete and Steel Bars Reinforcement Corrosion“, Australian Journal of Basic and Applied Sciences, 464-467, 2013.



ELK
Asia Pacific Journals

www.elkjournals.com

[9] Madhavi, T. Ch. et al (2013), „Effect of Multiwalled Carbon Nanotubes on Mechanical Properties of Concrete“, International Journal of Scientific Research, Vol.2, Issue 6, June 2013, 166-168.

[10] Rajmane, N.P. et al (2013), „Effect of Addition of Nano-Silica to Portland Cement Mortar, with and without Silica Fume“, ICI Journal, vol 14, No.2, July-September, 7-16